EXPONA® COMMERCIAL

Expona Commercial是豪华乙烯基瓷砖的集合，复制了天然木材，板岩和大理石的美感，以及其他创意和用于重型商业区域的创新效果。



Gauge 厚度	EN 428/EN ISO 24346	2.5mm
Wear Layer 耐磨层	EN 429/EN ISO 24340	0.55mm
Plank Size 板材尺寸	EN 427/EN ISO 24342	36 @ 101.6 x 914.4mm =3.34m² 24 @ 152.4 x 914.4mm = 3.34m² 18 @ 152.4 x 1219.2mm = 3.34m² 15 @ 184.2 x 1219.2mm =3.37m² 14 @ 203.2 x 1219.2mm = 3.46m² 12 @ 184.2 x 1524mm =3.37m² 12 @ 76.2 x 914.4mm 12 @ 101.6 x 914.4mm 12 @ 152.4 x 914.4mm } =3.62m²
Tile Size 块材尺寸	EN 427/EN ISO 24342	12 @ 304.8 x 914.4mm = 3.34m² 11 @ 203.2 x 1524mm = 3.41m² 9 @ 609.6 x 609.6mm =3.34m² 8 @ 457.2 x 914.4mm =3.34m² 12 @ 152.4 x 609.6mm 12 @ 304.8 x 304.8mm 6 @ 304.8 x 609.6mm } =3.34m²
Total Weight 总重量	EN 430/EN ISO 23997	4290g/m²
General Performance 一般性能	EN 649 EN ISO 10582	Conforms 符合 Conforms 符合
Use Area 使用区域	EN 685/EN ISO 10874	23 33 42
Reaction to Fire 防火等级	EN 13501-1	Class Bfl-S1 ; Bfl-S1级
Abrasion Resistance 耐磨等级	EN 660-2 EN ISO 10582	Group T; T组 Type 1; 类型1
Slip Resistance 防滑等级	EN 13893 DIN 51130 AS/NZS 4586 For safety flooring with sustainable wet slip resistance, refer to Expona Control or the Polysafe ranges. 对于具有可持续抗湿滑性的安全地板，请参阅Expona Control或Polysafe系列。	Class DS (dry condition) R10 R10
Indentation Residual 残余压痕	EN 433/EN ISO 24343-1	≤0.05mm
Dimensional Stability 尺寸稳定性	EN 434/EN ISO 23999	≤0.1% max
Thermal Conductivity 导热系数	ISO 1264-2	Suitable for underfloor heating. Max 27°C. ; 适用于地板采暖。最高27°C。
Light Fastness 耐光性	ISO 105-B02	(Method 3) ≥6
Castor Chair (continuous use) 脚轮椅（连续使用）	EN 425/ISO 4918	yes, type W, EN 12 529
Electrical behaviour (body voltage) 电性（本体电压）	EN 1815	≤2kV Classified as 'antistatic'
VOC Emissions 挥发性有机化合物排放	Indoor Air Comfort GOLD AgBB VOC test FloorScore	Eurofins certified product Very low emissions Certified product
Responsible Sourcing 负责任的采购	BES 6001 SA 8000	Very Good; 很好 Approved factory: 已被批准的产商

环保地板 - Polyflor Expona Commercial PUR达到BRE全球环境A +等级（证书编号：ENP 429）。通用EN可根据要求提供15804环境产品声明（EPD）。
Expona Commercial PUR是100%可回收的，平均包含40%的回收材料。可通过Recofloor方案回收。请访问www.polyflor.com/sustainability。

PUR - Expona Commercial PUR具有高质量的交联聚氨酯增强材料，可进行紫外线固化，从而提供低成本，免抛光的维护地板的使用寿命制度。

有关处理和安装，粘合剂，维护，应用，耐化学性和产品保修的信息，请咨询Polyflor客户技术服务部+44（0）161 767 1912，或发送电子邮件至tech@polyflor.com。
显示的数据在打印时是正确的。有关最新信息，请访问我们的网站polyflor.com。
装饰和阴影可能与所示样品略有不同。

100% RECYCLABLE
40% RECYCLED MATERIAL

BRE ENP 429 ENVIRONMENTAL RATING

EPD

Recofloor™ Vinyl Take-Back Scheme

POLYFLOR PUR POLISH FREE

BES 6001 Responsible Sourcing www.greenbooklive.com

EUROFINS INDOOR AIR COMFORT GOLD CERTIFIED PRODUCT

floorscore

NBS BIM

NBS Plus

SGS SGS

CE EN 14041

POLYFLOR™ COVERING THE WORLD

UK Sales Direct: +44 (0)161 767 1122 | Export Sales Direct: +44 (0)161 767 1913
Sample Requests: +44 (0)161 767 2551 | email: info@polyflor.com | www.polyflor.com

James Halstead™ FLOORING

June 2017